

TECH DATA SHEET

1. PRODUCT NAME

Touch 'n Seal® Quick Cure HY (High Yield) Polyurethane Foam Sealant

Touch 'n Seal[®] Quick Cure RX (Reduced Expansion) Polyurethane Foam Sealant

2. MANUFACTURER

FAX

Convenience Products 866 Horan Dr., Fenton, MO 63026 USA

(636) 349-5855 (800) 325-6180 (636) 349-5335

E-mail support@touch-n-seal.com Website: www.touch-n-seal.com

3. PRODUCT DESCRIPTION

Touch 'n Seal Quick Cure foams are high performance, single component, moisture curing, Class 1 fire retardant, expanding polyurethane sealants. Quick Cure sealants are available in both straw dispensed aerosol cans and larger cylinders with hoses and applicators.

Quick Cure sealants are available in High Yield (HY) and Reduced Expansion (RX) formulations. Use Quick Cure HY when high expansion is needed to fill and seal larger gaps and cracks. Use Quick Cure RX when requiring controlled dispensing rate and less post expansion. Both formulations are tack free in 30 minutes or less, can be trimmed in 1 hour and are fully cured in about 24 hours, depending upon humidity and temperature.

Basic Use

Use Quick Cure Polyurethane Foam Sealants to permanently air seal and insulate gaps and cracks to block drafts, moisture and insects while improving comfort and reducing energy usage in commercial, industrial, agricultural and residential applications. Use to seal around plumbing, ventilation outlets, electrical junctions, between sill plates and concrete slabs, or anywhere you need a fast, economical air-sealing moisture barrier.

For fireblock and sealing applications refer to ICC-ES 1926 detail.

Quick Cure foams provide permanent insulating and air sealing solutions to building component materials including wood, masonry, insulating foam boards, metal, wire insulation, plastics and sheetrock.

Use Touch 'n Seal Poly-Clean Foam Cleaner to clean wet Quick Cure foams from hands, tools and foam applicator guns.

Composition & Materials

Touch 'n Seal Quick Cure polyurethane one-component expanding foam sealants are permanent, hypoallergenic and dry within minutes of application. Quick Cure foams are non-toxic and will not decompose with age.

Sizes

Quick Cure HY Straw Foam Item # 4004521212 - 12 ounce (340 gm)

Quick Cure HY Straw Foam Item # 4004521224 - 24 ounce (680 gm)

Quick Cure HY Foam Complete Item # 4004518100 - 10 pounds (4.54 kg)

Quick Cure HY Foam Cylinder Only Item # 4004518101 - 10 pounds (4.54 kg)

Quick Cure HY Foam Complete Item # 4004518160 - 16 pounds (7.26 kg)

Quick Cure HY Foam Cylinder Only Item # 4004518161 - 16 pounds (7.26 kg)

Quick Cure RX Foam Complete Item # 4004510950 - 10 pounds (4.54 kg)

Quick Cure RX Foam Cylinder Only Item # 4004510951 - 10 pounds (4.54 kg)

Quick Cure RX Foam Complete Item # 4004516900 - 16 pounds (7.26 kg)

Quick Cure RX Foam Cylinder Only Item # 4004516901 - 16 pounds (7.26 kg)

Features/Benefits

- · Multiple package sizes
- · Easy to use
- · Class 1 fire retardant
- Provides a permanent seal against air, moisture and insect infiltration
- Easier to use than caulk type penetration sealants
- Bonds to common building materials including wood, concrete, insulating foam boards, metal, plastics and sheetrock
- Available in both straw and cylinder dispensing systems
- Reduces energy loss
- No ozone depleting chemicals
- Does not shrink
- Does not trap moisture, dust and allergens as does fiberglass insulation
- Expands to fill gaps and cracks, reducing air exchanges
- Reduces use of fossil fuels and improves air quality
- Helps to reduce Greenhouse Gas Emissions
- · Closed cell structure

Limitations

- Do not expose to temperatures above 240°F (116°C), open flames or sparks
- Not for exposure to ultraviolet light
- Chemicals must be 50°-100°F (10°-38°C) prior to application
- Do not store in temperatures above 120°F (49°C)
- Always refer to local building code regulations
- Do not leave product exposed; cover with approved facings
- Propellant in 12 & 24 ounce straw foam is flammable; read MSDS and do not use near high heat, sparks or open flame



· Not a fire stop material

4. TECHNICAL DATA

Applicable Standards

- ASTM E-96 Water Vapor Transmission
- ASTM C-273 Shear Strength
- ASTM C-273 Shear Strain
- ASTM C-518 R-Value
- ASTM E-814 Firestop Penetration
- ASTM C-1536 Yield
- ASTM D-1621 Compressive Strength
- ASTM D-1622 Density
- ASTM D-1623 Tensile Strength
- ASTM D-2856 Closed Cell Content
- UL 1715 Fire Test
- UPB26-3 Corner Room Fire Test

Approvals/Certifications

- · International Building Code
- International Residential Code
- BOCA National Building Code
- 1999 Standard Building Code
- 1997 Standard Building Code
- ICC-Evaluation Services
- California Bureau of Home Furnishings and Insulation
- Underwriters Laboratories Classified Caulking & Sealants

Physical/Chemical Properties See Table. Test data available upon request.

Shelf Life

12 months in unopened container when stored between 60°-90°F (16°-32°C), in a dry, well-ventilated area.

Storage & Disposal

Keep containers tightly closed in a cool, well-ventilated area. Ideal storage temperature is 60°-90°F (16°-32°C). Storage above 90°F (32°C) will reduce shelf life. Do not store at temperatures greater than 120°F (49°C). Do not expose containers to conditions that may damage, puncture, or burst the containers. Dispose of leftover material/containers in accordance with Federal, state and local regulations. See Material Safety Data Sheet for more information.

5. INSTALLATION/APPLICATION

Always refer to local building codes prior to application of Touch 'n Seal® foam sealants.

The Touch 'n Seal® Quick Cure one-component expanding foam sealant can be applied to and will adhere to almost any traditional construct surfaces including wood, masonry, insulating





TECH DATA SHEET

foam boards, metal, plastics and sheetrock.

Surfaces to receive Touch 'n Seal foam sealants must be dry, clean and free of dust, dirt, grease and other substances that may inhibit proper adhesion. For best results apply Touch 'n Seal[®] Quick Cure expanding foam sealant when surface and ambient temperatures are between 60°-100°F (16°-38°C). Temperature of chemical contents must be between 50°F-100°F (10°C-38°C) before dispensing.

Use all chemical contents within 30 days of initial dispensing.

Keep out of reach of children. Always wear proper personal protective equipment, including gloves, clothing and eyewear. Use in well-ventilated area.

Please refer to manufacturer's instructions or request a faxed set of instructions from Convenience Products by calling Customer

Service at 800-325-6180.

6. AVAILABILITY & COST

Availability

Touch 'n Seal polyurethane foams are available throughout the U.S., Canada, Mexico and the world. Contact Convenience Products Customer Service at 800-325-6180 or FAX 636-349-1708 for distributor information.

Cost

Contact Convenience Products for local distributors who can provide cost and delivery information.

7. WARRANTY

Convenience Products warrants its Touch 'n Seal products to be free of defects in workmanship and function.

Convenience Products is not liable for any

incidental, consequential or any other damages beyond the description herein, however, certain states have specific laws regarding limitation on incidental or consequential damages, in which case, and you may have other legal rights.

8. MAINTENANCE

None

9. TECHNICAL SERVICES

Technical assistance, including more detailed information, product literature, test results, assistance with preparing project specifications and application training is available by contacting Convenience Products.

10. FILING SYSTEMS

Additional information is available from the manufacturer upon request.

The information contained herein was accurate at the time of publishing. Please refer to the Touch 'N Seal website for the latest information.

TYPICAL PROPERTIES OF TOUCH 'N SEAL QUICK CURE POLYURETHANE CLASS 1 FOAM SEALANT

Container Sizes	12 & 24 ounce (340 & 680 gm) Straw Foam	10 & 16 pound (4.54 & 7.26 kg) Cylinder Foam
Shelf Life	1 year; unopened container	1 year; unopened container
Dry time/Tack Free Time	< 30 minutes (50% R.H., 70°F)	< 15 minutes (50% R.H., 70°F)
Fully Cured	24 hours (50% R.H., 70°F)	24 hours (50% R.H., 70°F)
Trimmable	< 1 hour	< 1 hour
ASTM E-96 Water Vapor Transmission	10 perm inches (25mm)	3.3 perm inch
ASTM C-273 Shear Strength	N/A	18 psi (1.27 kg/cm ²)
ASTM C-273 Shear Strain	N/A	57%
ASTM C-518 R-Value	4.9 /in. (25 mm)	4.5 /in. (25 mm)
ASTM E-814 Fire Tests of Penetration	, ,	, , ,
Firestop Systems	Pass	Pass
ASTM C-1536 Yield	12 oz (340gm) ¼ in. (6.4mm) dia. bead – 918 ft. (280m) 3/8 in. (9.5mm) dia. bead – 408 ft. (124m)	10 lb HY 1/4 in. (6.4mm) dia. bead – 15,300 ft. (4,663m) 3/8 in. (9.5mm) dia. bead – 6,800 ft. (2,072m) 16 lb HY 1/4 in. (6.4mm) dia. bead – 24,400 ft. (7,437m) 3/8 in. (9.5mm) dia. bead – 10,900 ft. (3,322m)
	24 oz (680gm) ¼ in. (6.4mm) dia. bead – 1,805 ft. (550m) 3/8 in. (9.5mm) dia. bead – 818 ft. (249m)	10 lb RX ¼ in. (6.4mm) dia. bead – 14,700 ft. (4,480m) 3/8 in. (9.5mm) dia. bead – 6,500 ft. (1,981m) 16 lb RX ¼ in. (6.4mm) dia. bead – 24,080 ft. (7,340m) 3/8 in. (9.5mm) dia. bead – 10,500 ft. (3,200m)
ASTM D-1621 Compressive Strength		11 psi (0.77 kg/cm²)
ASTM D-1622 Density	1.75 +/25 pcf (20.8 +/1 4.0 kg/m ³)	1.3 - 1.8 pcf (20.8 - 28.8 kg/m ³)
ASTM D-1623 Tensile Strength Percent elongation at break	N/A	33 psi (0.02 kg/cm²) 10%
UL 1715 Fire Test		
Flame Spread	10	20
Smoke Development	15	25
UPB26-3 Corner Room Fire Test	N/A	N/A
ASTM D-2856 Closed Cell Content	N/A	70%
International Building Code	Conforms	Conforms
International Residential Code	Conforms	Conforms
BOCA National Building	Conforms	Conforms
1999 Standard Building Code	Conforms	Conforms
1997 Standard Building Code	Conforms	Conforms
ICC-ES	ESR-1926	ESR-1926
California Bureau of Home Furnishings and Insulation	Listed	Listed
Underwriters Laboratories Classified Caulking & Sealants	R14175	R14175